

PROPERTY	UNIT	GUARANTEE	LIMIT	TEST METHOD
Viscosity, Efflux time (4 mm 25°C)	s	Class 2	<200 (23±10)	EN 12846-2
Solubility	%	Class 2	>99	EN 12592
Flash Point	°C	Class 7	>60	EN ISO 13736 EN ISO 2719 EN ISO 2592
Adhesivity with referance aggregate		Class 0	No Requirement	EN 15626
Distillation :				
Total distillate to 360°C		Class 7	<55	
% of total distillate fraction distilling at 190°C		Class 2	<5	
% of total distillate fraction distilling at 225°C		Class 2	<15	EN 13358
% of total distillate fraction distilling at 260°C	% vol	Class 1	TBR	
% of total distillate fraction distilling at 315°C		Class 1	TBR	
Penetration at 25°C	0.1 mm	Class 0	No Requirement	EN 1426
Softening Point	°C	Class 0	No Requirement	EN 1427

This product is produced in İzmit, İzmir, Kırıkkale ve Batman Refineries.