

**PRODUCT SPECIFICATION
SPINDLE SLACK WAX (*)1410**

Property	Test Unit	Guarantee	Limit	Test Method	
				ASTM	IP
Density (at 15 °C)	Kg/m ³	779,3-834,4		D 1298 D 4052	
Color, (10 % Dilute)	ASTM	0,5	Max	D 1500	
Flash Point	°C	160	Min	D 92	
Melting Point	°C	40	Min	D 127	
Oil Content	wt %	20	Max	D 721	
Viscosity (at 100°C)	cSt	2,0-4,8		D 445	
Sulfur	wt %	0,3	Max		336
Conradson Carbon Residue	wt %	0,1	Max	D 4530	

(*) This product is produced only in İzmir Refinery.