

PROPERTY	UNIT	GUARANTEE	LIMIT	TEST METHOD
Penetration at 25°C	0.1 mm	Class 5	40-100	EN 1426
Softening Point	°C	Class 7	≥55	EN 1427
Cohesion				
Force ductility (50 mm/min traction)	J/cm <sup>2</sup>	Class 2	≥ 3 at 5°C	EN 13589
Elastic recovery at 25°C	%	Class 1	TBR	EN 13398
Resistance to hardening:				
Retained penetration	%	Class 7	≥60	EN 12607-1
Increase in softening point	°C	Class 2	≤ 8	
Decrease in softening point <sup>a</sup>	°C	Class 1	TBR	
Change of mass <sup>b</sup>	%	Class 2	≤ 0.3	
Flash Point	°C	Class 2	≥ 250	EN ISO 2592

<sup>a</sup> Softening point after EN 12607-1 (RTFOT) may increase or decrease. If there is a decrease in softening

point, the result will be reported.

<sup>b</sup> Change of mass can be positive or negative.